



Por-A-Kast

Amber-Cast

Applications

Por-A-Kast Amber-Cast is used to make castings from rigid and flexible molds. Some of the most common uses of Amber-Cast are point-of-purchase displays, rapid prototypes, special effects, taxidermy, and sculpture reproductions. However, Amber-Cast can be used for any application that requires lightweight, hard plastic.

Characteristics

Por-A-Kast Amber-Cast is a two-part polyurethane casting system. Amber-Cast is mixed one-to-one by volume and cures at room temperature. Amber-Cast begins to gel in approximately 2 minutes, and cures to an amber color.

Instructions for Use

Prepare Mold

Before you begin to cast a polyurethane mold, you must prepare the mold by applying the appropriate release agent (we recommend Synlube 531). Apply release agent sparingly, while coating all internal surfaces of the mold. Too much release agent may cover the details of the mold. You should allow the release agent to dry approximately 10 minutes before you pour the casting. Please note that silicone molds do not require a release agent. If you want to use an in-mold paint, like CilCoat, you should apply it after the release agent dries.

Measure Curative and Prepolymer

Note: Por-A-Kast Amber-Cast provides approximately 2 minutes for you to mix and pour the casting before it begins to gel.

Using two clean, dry, plastic containers of equal size, measure equal amounts of the curative (part A) and the prepolymer (part B). If you want to use a filler or powder, use another clean, dry, plastic container to measure the filler or powder.

Do not measure more Por-A-Kast than you can pour within its pot life. If you have a large mold that requires more Amber-Cast than you can pour in 2 minutes, you may use a rotational casting method or pour Amber-Cast more than once (if you pour it more than once, you should do so immediately).

Mix Filler or Powder into Curative and Prepolymer

If you want to use a filler or powder, mix half of the filler or powder into the curative and the remaining half of the filler or powder into the prepolymer *before* you mix the curative and prepolymer together.

Mix Curative and Prepolymer

Note: Por-A-Kast Amber-Cast provides approximately 2 minutes for you to mix and pour the casting before it begins to gel.

After you prepare the mold, measure the curative and prepolymer, mix the filler or powder into the curative and prepolymer (optional), you are ready to pour the curative and prepolymer into another clean, dry, plastic container. Combine the two ingredients for approximately 30 seconds, being careful to prevent air bubbles from forming. Use a plastic or metal spatula to mix Amber-Cast.

Pour Casting

Note: Por-A-Kast Amber-Cast provides approximately 2 minutes for you to mix and pour the casting before it begins to gel.

Although Amber-Cast gels quickly, you should take your time to carefully pour it into the mold. The best way to pour a casting with Amber-Cast is to tilt your mold slightly and pour into one spot of the mold. Pour slowly so that any air bubbles that may have formed during mixing can break over the lip of the container as it pours out.

Demold and Cure Casting

Once you have poured your casting, do not disturb the mold or demold the casting for 60 minutes. We recommend that you allow your cast to cure for 24 hours for best results. After Amber-Cast has cured, you may turn, drill, grind, sand, and paint it.

Properties

Curative (Part A) and Prepolymer (Part B)

2003 Curtain Pole Road, P.O. Box 5413 · Chattanooga, Tennessee 37406
Office: 423.697.0499 · Fax: 423.697.0437



The following table lists the properties of the curative and prepolymer before they have been mixed.

Property	Curative (Part A)	Prepolymer (Part B)
Mix Ratio by Volume	1	1
Shelf Life	12 Months	12 Months
Specific Gravity @ 75° F (24° C)	1.05	1.13
Viscosity @ 75° F (24° C), CPS	300	90

Mixed Curative (Part A) and Prepolymer (Part B)

The following is a list of the properties of Por-A-Kast Amber-Cast after the curative and prepolymer have been mixed.

Property	Time	Temperature
Mix Time	30 Seconds	75° F (24° C)
Pot Life*	1 Minute	75° F (24° C)
Gel Time*	2 Minutes	75° F (24° C)
Cure Time*	24 Hours	75° F (24° C)
Demold Time*	1 Hour	75° F (24° C)

*Pot life, gel time, cure time, and demold time vary depending on mass, mold temperature, and component temperature.

Cured Por-A-Kast

The following table lists the properties of Por-A-Kast Amber-Cast after it has cured.

Property	Cured Product
Color	Amber
Rebound, Bashore, ASTM D2632-74, %	46
Reversion Temperature	270° F (132° C)
Shore Hardness, ASTM D 2240-75	D72±2
Tear, Die C, ASTM D624-73, pli	299
Tear, Split, ASTM D470-71, pli	131
Ultimate Tensile, ASTM D412-80, psi	3378
Ultimate Elongation	Less than 10%

Storage and Handling

Keep the Por-A-Kast Amber-Cast containers tightly closed when not in use and store at temperatures between 60–90° F (16–32° C). Do not expose the curative or prepolymer to moisture! If moisture contaminates Por-A-Kast Amber-Cast, it will not cure. If these storage requirements are met, Por-A-Kast Amber-Cast carries a shelf life warranty of six months.

Be sure to read the *Material Safety Data Sheet* that comes with Por-A-Kast Amber-Cast. When working with Por-A-Kast Amber-Cast, please observe the following safety precautions.

- Use only in well-ventilated areas.
- Wear chemically resistant rubber gloves, safety glasses, and an apron.
- Avoid prolonged or repeated contact with skin.
- In the case of skin contact, wipe affected area with isopropyl alcohol, followed by soap and water.
- In the case of eye contact, flush eyes with water for 15 minutes and consult a physician.
- If swallowed, drink one to two glasses of water and seek medical attention immediately.

Por-A-Kast Amber-Cast Product Bulletin

The conditions for your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. PUMA Polymers has not necessarily done such testing. All information is given without warranty or guarantee. It is expressly understood and agreed that customer assumes and hereby expressly releases PUMA Polymers from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind PUMA Polymers. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.