



MONOPRIME™ Red

Description

A one component, single coat adhesive for bonding urethanes to metal and/or other substrates. Monoprime Red is excellent as a bonding agent for thermoplastic polyurethane. It can be used as protective coating for metal, polyurethane, epoxy, polyester, and fiberglass compounds.

Properties of Monoprime Red

The following table explains the properties of Monoprime Red.

Property	Monoprime Red
Bond Temperature Range	75°–450°F (24°–232° C)
Color	Red
Dry Film	1 Mil
Flash Point (Tag Closed Cup)	22° F (-6° C)
Non-volatile Solids	24%
Shelf Life at 75°F (24° C)	6 Months (Minimum)
Specific Gravity	0.93
Theoretical per Gallon Coverage	300 Ft ²
Viscosity (Brookfield)	500 CPS
Weight	7.7 Lbs. (3.5 Kg)

Diluent of Monoprime Red

The best diluent is 10 parts (by weight) of Toluene to 30 parts (by weight) of Methyl Ethyl Ketone.

Applying Monoprime

You can apply Monoprime Red by brushing, dipping, or spraying. You should make sure that the surface is clean of the part is clean before applying Monoprime Red. For best results, sandblast or degrease the part with a solvent (M.E.K., Naphtha, Toluene). For optimum adhesion, you should prebake the coated part for one hour at 300° F (149° C). The dry film stability is excellent. Store coated part away from dust and other contaminants.

Monoprime Red Product Bulletin

The conditions for your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Puma Polymers. All information is given without warranty or guarantee. It is expressly understood and agreed that customer assumes and hereby expressly releases Puma Polymers from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Puma Polymers. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

VI-060809